

Designation: **C90 - 16a**

## Standard Specification for Loadbearing Concrete Masonry Units<sup>1</sup>

This standard is issued under the fixed designation C90; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers hollow and solid (see 5.3 and 5.4) concrete masonry units made from hydraulic cement, water, and mineral aggregates with or without the inclusion of other materials. There are three classes of concrete masonry units: Normal Weight, Medium Weight, and Lightweight. These units are suitable for both loadbearing and nonloadbearing applications.

1.2 Concrete masonry units covered by this specification are made from lightweight or normal weight aggregates, or both.

NOTE 1—The requirements of this specification have been researched, evaluated, and established for over a century, resulting in the physical properties and attributes defined here. These requirements are uniquely and solely applicable to concrete masonry units manufactured on equipment using low or zero slump concrete and the constituent materials defined herein. Many performance attributes of concrete masonry units are indirectly accounted for, or inherently reflected within, the requirements of this specification without direct measurement, assessment or evaluation. Applying the requirements of this specification to products that may be similar in appearance, use, or nature to those covered by this specification may not address all pertinent physical properties necessary to ensure performance or serviceability of the resulting construction in real-world applications under typical exposure environments. Product manufactured using alternative materials, manufacturing methods or curing processes not covered by this specification should not be evaluated solely using the requirements in this specification. However, developers of new products can consider the property requirements of this specification as a beginning benchmark for unit performance. It is reasonable to test new products for system performance as well as unit performance.

1.3 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 2—When particular features are desired such as surface textures

<sup>1</sup>This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved Dec. 15, 2016. Published January 2017. Originally approved in 1931. Last previous edition approved in 2016 as C90-15. DOI: 10.1520/C0090-16A.

for appearance or bond, finish, color, or particular properties such as density classification, higher compressive strength, fire resistance, thermal performance or acoustical performance. These features should be specified separately by the purchaser. Suppliers should be consulted as to the availability of units having the desired features.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- C33/C33M Specification for Concrete Aggregates
- C140/C140M Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C150/C150M Specification for Portland Cement
- C330/C330M Specification for Lightweight Aggregates for Concrete Masonry Units
- E426 Test Method for Linear Drying Shrinkage of Concrete Masonry Units
- C595/C595M Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C979/C979M Specification for Pigments for Integrally Colored Concrete
- C989/C989M Specification for Slag Cement for Use in Concrete and Mortars
- C1157/C1157M Performance Specification for Hydraulic Cement
- C1232 Terminology of Masonry
- C1240 Specification for Silica Fume Used in Cementitious Mixtures
- C1314 Test Method for Compressive Strength of Masonry Prisms
- E519/E519M Test Method for Diagonal Tension (Shear) in Masonry Assemblages
- E72 Test Methods of Conducting Strength Tests of Panels for Building Construction

### 3. Terminology

3.1 Terminology defined in Terminology C1232 shall apply for this specification.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.